




KNAUFCEILING
Solutions

阿姆斯壮 雅韵®条形板



- 阿姆斯壮雅韵矿棉天花板表面采用无方向性花纹设计，为您提供成本最优的方案同时具有良好的吸音降噪功能，并有多种尺寸和边角处理可供选择
- 杰出的吸音效果 NRC 0.60
- 良好的反光度 85%
- 适用于办公环境，公共区域



边角类型		SL2半明半暗可开启系统 	明架平板 	切角跌级 														
厚度 (mm)		16/17	16/17	16/17														
尺寸 (mm)		300 x 1200 300 x 1800 600 x 1200 400 x 1800	300 x 1200 300 x 1800 600 x 1200 400 x 1800	300 x 1200 300 x 1800 600 x 1200 400 x 1800														
龙骨系统		SL2配暗架T型龙骨	尖峰顶端2000型龙骨	尖峰顶端4000型凹槽龙骨														
质量		4.4 千克/平方米 (0.9 磅/平方英尺)																
颜色		白色																
隔音		隔音等级 CAC = 35 (BOARD)																
吸音性能		$\alpha_w = \mathbf{0.55}$ as per EN ISO 11654:1997 Class D <table border="1"> <thead> <tr> <th>Frequency f (HZ)</th> <th>125</th> <th>250</th> <th>500</th> <th>1000</th> <th>2000</th> <th>4000</th> </tr> </thead> <tbody> <tr> <td>as</td> <td>0.24</td> <td>0.25</td> <td>0.52</td> <td>0.82</td> <td>0.76</td> <td>0.72</td> </tr> </tbody> </table> NRC = 0.60 as per ASTM C423-17			Frequency f (HZ)	125	250	500	1000	2000	4000	as	0.24	0.25	0.52	0.82	0.76	0.72
Frequency f (HZ)	125	250	500	1000	2000	4000												
as	0.24	0.25	0.52	0.82	0.76	0.72												
防火等级		US: Class A - Flame Spread 25 or Under; A级 (火焰蔓延度25或以下,美国标准) Class 0 / Class 1 based on BS 476 Pt - 6 & 7;英国标准 Class A (China standard - GB/T 14402); A级 (适用于燃烧热值实验, 中国标准)																
反光度		85%																
热阻值		平均R Factor - 1.70 (英制) 平均R Factor - 0.30 (公制)																
防潮等级		防潮等级 RH99																
可持续性		43% 回收材料 中国环境标志 中国绿色建筑委员会 符合LEED计分要求																

