



KNAUFCEILING
Solutions

阿姆斯壮 极品+条形板



- 阿姆斯壮极品+矿棉天花板拥有更为细腻，时尚的白色外观，同时拥有多种尺寸和边角处理可供选择，是需要卓越吸音性能的场所的最佳解决方案
- 杰出的吸音效果 NRC 0.70
- 杰出的隔音效果 CAC 35
- 良好的反光度 88%
- 更适用于办公，零售，医疗，教育环境



边角类型		K2C2半明半暗可开启系统 	SL2半明半暗可开启系统 	加强型斜角跌级 	切角跌级 														
厚度 (mm)		19	19	19	19														
尺寸 (mm)		300 x 1200 400 x 1500 300 x 1500 400 x 1800 400 x 1200 600 x 1200	300 x 1200 400 x 1500 300 x 1500 400 x 1800 400 x 1200 600 x 1200	300 x 1200 400 x 1500 300 x 1500 400 x 1800 400 x 1200 600 x 1200	300 x 1200 400 x 1500 300 x 1500 400 x 1800 400 x 1200 600 x 1200														
龙骨系统		Channel K2C2 配暗C型龙骨	SL2配暗架T型龙骨	尖峰顶端2000型龙骨	尖峰顶端4000型 凹槽龙骨														
质量		5.32 千克/平方米 (1.09 磅/平方英尺)																	
颜色		白色																	
隔音		隔音等级 CAC = 35																	
吸音性能		$\alpha_w = 0.60$ as per EN ISO 11654:1997 Class C <table border="1"> <thead> <tr> <th>Frequency f (HZ)</th> <th>125</th> <th>250</th> <th>500</th> <th>1000</th> <th>2000</th> <th>4000</th> </tr> </thead> <tbody> <tr> <td>α_s</td> <td>0.44</td> <td>0.46</td> <td>0.63</td> <td>0.83</td> <td>0.81</td> <td>0.83</td> </tr> </tbody> </table> NRC = 0.70 as per ASTM C423-17				Frequency f (HZ)	125	250	500	1000	2000	4000	α_s	0.44	0.46	0.63	0.83	0.81	0.83
Frequency f (HZ)	125	250	500	1000	2000	4000													
α_s	0.44	0.46	0.63	0.83	0.81	0.83													
防火等级		US: Class A - Flame Spread 25 or Under; A级 (火焰蔓延度25或以下,美国标准) Class 0 / Class 1 based on BS 476 Pt - 6 & 7;英国标准 Class A (China standard - GB/T 14402); A级 (适用于燃烧热值实验, 中国标准)																	
反光度		88%																	
热阻值		平均R Factor - 1.70 (英制) 平均R Factor - 0.30 (公制)																	
防潮等级		防潮等级 RH99																	
耐久性		耐刮擦																	
可清洁性		可擦洗 干布擦洗																	
可持续性		42% 回收材料 中国环境标志 符合LEED计分要求																	

