


ARMSTRONG SCHOOL ZONE SMART®



- Armstrong SCHOOL ZONE SMART provides an excellent sound absorption solution through effective shorten reverberation time (RT), then improve speech intelligibility
- Good sound absorption NRC 0.60
- Excellent light reflectance (85%)
- Ideal for healthcare environments



ARMSTRONG SCHOOL ZONE SMART®



Edge details	Board	Tegular 24	Tegular 15 BE
_			
	24 24	24 24	15
Thickness (mm)	15	15	15
Dimensions (mm)	600 x 600	600 x 600	600 x 600
System	PeakForm 888 Prelude XL 32	PeakForm 888 Select	Select PeakForm Suprafine XI
Weight	3.19 kg/m ² (0.66 lbs/SF)		
Colour	White		
Sound attenuation	CAC = 33		
Sound absorption	$a_w = 0.55$ as per EN ISO 11654:1997 Class D		
	as 0.38 0.30	500 1000 2000 4000 0 0.51 0.84 0.75 0.71	
	NRC = 0.60 as per ASTM C423	3-17	
Fire reaction	US: Class A - Flame Spread 25 or Under; Class O / Class 1 based on BS 476 Pt - 6 & 7; Class A (China standard - GB/T 14402)		
Light reflectance	85%		
Thermal conductivity	R Factor - 1.50 (BTU units) R Factor - 0.26 (Watts units)		
Humidity resistance	RH95		
Sustainability	Recycled Content China Green Product Label	Member of China GBC Qualify for LEED Credit	is



